World Resources Company

Form: FM-M01

RECYCLABLE MATERIAL PROFILE

EXHIBIT A

Generator Name: Alaskan Copper Works | **Company I.D. #: 22149-001-01**

A. Generator Information

1. Address: 3200 Sixth Avenue South
   Seattle
   WA 98124
2. Contact: Gerald Thompson
   Title: Environmental Assistant
3. Material EPA Waste Code: F006
4. Generator's EPA I.D. Number: WAD980738546
5. Generator's State I.D. Number:

B. Recyclable Material Characteristics

1. **Color(s):** Brown
2. **Odor** (none,mild,strong): None
   Description of Odor:
3. **Moisture** (wet,damp,dry): Wet
   Percent Solids: 25.4
4. **pH** (EPA SW 846, method 9040/9045): pH: 8.90 @ 21.7 °C
5. **Ignitability** (40 CFR § 261.21): ☑ PASS ☐ FAIL
6. **Texture** (similar to): ☑ Wet Clay ☐ Dry Clay ☐ Sand ☐ Powder ☐ Other
7. **Appearance**: ☑ Homogenous ☐ Bilayered ☐ Multilayered
8. **Organic Vapors**: ☐ Present ☑ Not Present (< 1ppm) If present, identify compounds and amount in ppm on a wet basis. ☑ Pass ☐ Fail
9. **Free Liquids** (EPA SW 846, Method 9095): ☑ Not Present ☐ Present
10. **Debris**: ☑ Not Present ☐ Present
11. **Reactivity**: ☑ Not Reactive ☐ Reactive
12. **Radionuclides** (ASTM D5928-96): ☑ Not Detected ☐ Detected
13. **Cyanide Gas HCN**: ☑ Not Detected ☐ Detected _____ ppm

C. Analytical Data

(Content on a dry weight basis in ppm or %)

	Constituent *		Content	Qualifier
1.	Aluminum [1]	Al	4693.8 ppm	
2.	Antimony [1,†]	Sb	28.0 ppm	
3.	Arsenic [1,†]	As	51.6 ppm	
4.	Barium [1,†]	Ba	79.8 ppm	
5.	Beryllium [1,†]	Be	< 20.0 ppm	
6.	Bismuth [1]	Bi	73.1 ppm	
7.	Cadmium [1,†]	Cd	< 40.0 ppm	M3
8.	Calcium [1]	Ca	10692.8 ppm	M3
9.	Chloride [4]	Cl^-	0.19 %	
10.	Chromium, Hexavalent [2]	Cr^{+6}	3570.3 ppm	
11.	Chromium, Total [1,†]	Cr	50907.2 ppm	
12.	Cobalt [1]	Co	862.1 ppm	
13.	Copper [1,†]	Cu	58518.2 ppm	
14.	Cyanide, Amenable [3,†]	CN^-	not analyzed	
15.	Cyanide, Total [3,†]	CN^-	< 39.4 ppm	Z2, Z3
16.	Fluoride [4]	F^-	0.35 %	
17.	Iron [1]	Fe	261595.0 ppm	
18.	Lead [1,†]	Pb	113.0 ppm	
19.	Magnesium [1]	Mg	1754.3 ppm	
20.	Manganese [1]	Mn	5705.8 ppm	
21.	Mercury [1]	Hg	< 6.6 ppm	
22.	Nickel [1,†]	Ni	72461.2 ppm	
23.	Selenium [1,†]	Se	< 100.0 ppm	
24.	Silver [1,†]	Ag	< 10.0 ppm	M3
25.	Thallium [1,†]	Tl	< 40.0 ppm	
26.	Tin [1,†]	Sn	< 200.0 ppm	M3, M6
27.	Zinc [1,†]	Zn	651.8 ppm	

*** Analytical Procedure References**

1. EPA Method SW846 3050 / 6010 (Digestion / Analysis)
2. EPA Method SW846 3060 / 7196 (Extraction / Analysis)
3. EPA Method SW846 9010 / 9213 or 9014 (Distillation / Anaylsis)
4. HNO_3 or H_2O_2 / EPA Method SW846 9056 (Digestion / Analysis)

† Licensed Constituent

D. Certification

I hereby certify that all information submitted in this profile is complete and accurate to the best of my knowledge and belief.

Signed: _____ **Date:** 5/29/07

Title: Laboratory Manager **AZ DHS #:** AZ0586

World Resources Company

Form: FM-M01

QA/QC DATA

EXHIBIT A

Generator Name: Alaskan Copper Works **Company I.D. #: 22149-001-01**

QA/QC Criteria: All analyses met method criteria unless otherwise noted.

Explanation of Data Qualifiers:

M3	The accuracy of the spike recovery value is reduced since the analyte concentration in the sample is disproportionate to spike level. The method control sample recovery was acceptable.
Z2	The low distilled standard did not meet method acceptance limits, the high distilled standard was acceptable.
Z3	The duplicate sample did not meet method acceptance limits due to the lack of sample homogeneity.
M6	Matrix spike recovery was high. Data reported per ADEQ policy 0154.000.

World Resources Company

Form: FM-M01

SAMPLE COLLECTION & ANALYSIS COMPLETION DATES

EXHIBIT A

Generator Name: Alaskan Copper Works | **Company I.D. #: 22149-001-01**

	Constituent		Sample Date	Completion Date	Sample Technician
1.	Aluminum	Al	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
2.	Antimony	Sb	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
3.	Arsenic	As	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
4.	Barium	Ba	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
5.	Beryllium	Be	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
6.	Bismuth	Bi	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
7.	Cadmium	Cd	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
8.	Calcium	Ca	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
9.	Chloride	Cl^-	01/22/2007 14:03	01/26/2007 12:00	KEVIN MCALISTER
10.	Chromium, Hexavalent	Cr^{+6}	01/22/2007 14:03	02/09/2007 15:00	KEVIN MCALISTER
11.	Chromium, Total	Cr	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
12.	Cobalt	Co	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
13.	Copper	Cu	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
14.	Cyanide, Amenable	CN^-			
15.	Cyanide, Total	CN^-	01/22/2007 14:03	02/05/2007 12:00	KEVIN MCALISTER
16.	Fluoride	F^-	01/22/2007 14:03	01/26/2007 12:00	KEVIN MCALISTER
17.	Iron	Fe	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
18.	Lead	Pb	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
19.	Magnesium	Mg	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
20.	Manganese	Mn	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
21.	Mercury	Hg	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
22.	Nickel	Ni	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
23.	Selenium	Se	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
24.	Silver	Ag	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
25.	Thallium	Tl	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
26.	Tin	Sn	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER
27.	Zinc	Zn	01/22/2007 14:03	03/28/2007 14:58	KEVIN MCALISTER

World Resources Company

8113 W. Sherman St.
Tolleson, AZ 85353-4025

Tel: 800.972.1955
Fax: 623.936.9164

May 29, 2007

Mr. Gerald Thompson
Environmental Assistant
Alaskan Copper Works
3200 Sixth Avenue South
Seattle, WA 98124

Dear Mr. Thompson:

In accordance with the recycling Agreement with your company, World Resources Company (WRC) provides a "RECYCLABLE MATERIAL PROFILE" (RMP) each contract year. Enclosed, for your records, is a completed RMP for the material generated at your plant. If a qualifier is indicated on the RMP, WRC has provided a quality assurance/quality control case narrative to validate the constituent's result(s).

The concentration of metals reported on the RMP is the total concentration of each metal on a dry basis. The recyclable material is prepared for analysis by first grid-sampling and then drying the selected sample in the laboratory oven at 103°-105° centigrade in order to obtain a homogeneous dry sample (Standard Methods For The Examination of Water and Wastewater, 15th Edition, published by the American Public Health Association 1980, Method 209A "Total Residue at 103°-105° centigrade"). Therefore, these results are generally higher than the concentrations of your material as it leaves your facility. You should multiply these dry concentrations by the decimal form of your percent solids (i.e. 50.0% = 0.50) to obtain the concentration of your material as it leaves your plant.

WRC appreciates your business and looks forward to a long and mutually beneficial recycling relationship. Please feel free to call me at (800) 972-1955 with any questions you may have regarding the enclosed RMP. Thank you for your interest in recycling.

Sincerely,

World Resources Company

Jason Hensley
Laboratory Manager

Enclosures